



Technical characteristics:

Base	MS Polymer
Consistency	Black Paste
Curing System	Moisture Cure
Specific Gravity (DIN 53479)	1.60 g/ml
Elongation at break (DIN 53504)	>200 %
Skin Formation (*) (20°C/65% R.H.)	Ca. 7 min.
Curing Rate (*) (20°C/65% R.H.)	2 - 3 mm/24h
Temperature Resistance (fully cured)	-40°C to +90° C
Tensile Strength at break	3.0 N/mm ²
Total solids content	100%
Consumption 290ml (with 3mm bead)	41 linear metres

(*) these values may vary depending on environmental factors such as temperature, moisture, and type of substrates

Product:

Rewmar Cap & cove is a high strength single component, adhesive. The MS-Polymer technology provides a chemically neutral and fully elastic adhesive. It is suitable for use on most substrates and construction materials.

Characteristics:

- High performance mechanical properties.
- Perfect for use in hospitals, schools and other public buildings
- Very fast curing and high bond strength on nearly all surfaces.
- Permanently flexible
- Very easy application.
- Sanitary applications.
- Free of isocyanates, solvents, halogens and acids.
- Minimal health and safety considerations.
- No staining of porous materials such as natural stone, granite, marble, etc.

Product Applications:

The bonding of all types of construction materials onto porous and non-porous surfaces. Typical applications include capping and coving profiles, skirtings in PVC and metal including trims that are not subjected to stress by footfall such as stair nosings. Rewmar Cap & Cove will also work on wet surfaces.

Application Method: apply the adhesive to the surface by means of an applicator gun. Application temperature: +5°C until +35°C.

The average coverage will be approximately 41 linear metres with a 3mm bead.

In some cases a larger bead may be required depending upon flatness of substrate.

Cleaning:

Rewmar Hand & Tool Wipes immediately after application and before curing.

Packaging:

Colour: Black

Packaging: 290ml cartridge

Shelf life: 24 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +35°C.

Resistance to chemical agents: Good resistance to water, aliphatic solvents, mineral oils, grease, diluted inorganic acids and alkalis. Poor resistance to aromatic solvents, concentrated acids, chlorinated hydrocarbons.

Substrates:

Rewmar Cap & Cove should be applied to a solid, dry, clean and smooth substrate. Residue of old adhesive or contaminants may affect adhesion and where possible must be removed. Loose or damaged surfaces should be repaired. **NOTE:** There is no adhesion onto PE, PP and PTFE (Teflon®).

Health and Safety Recommendation:

Apply the usual industrial hygiene.

NOTE: This product is suitable for use in high-rise apartments including stairwells and communal areas