



Multi Purpose Primer Technical Data Sheet

Product:

Colour: White

Packaging: 5 Litre container

Flexyfix Multi Purpose Primer is a one part ready to use synthetic dispersion primer suitable for use on porous and non-porous subfloors to aid adhesion.

Suitable substrates include concrete, sand/cement, calcium sulphate (anhydrite) chipboard, plywood and similar substrates.

Only for indoor use

Technical data:

Base	Synthetic Dispersion
Curing system	Air Dry
Consistency	Liquid
Colour	White - Transparent when fully dry
Specific gravity (g/cm ³)	Approx. 1g/mL
Drying Time @ 21°C and 50% RH	Up to 30 minutes*
Semi Porous	Approx. 30 - 60 minutes
Calcium Sulphate (Anhydrite)	12 to 24 Hours
Application Temperature	10°C to 25°C
Temperature Resilience	-5°C to +55°C
Application rate	100 - 200 ml/m ² Porosity Dependant

* This can vary according to environmental circumstances such as temperature, humidity, substrate etc.

Characteristics:

- One component,
- Ready to use
- Easy to apply,
- Solvent free
- Fast drying
- Binds and consolidates substrates
- Reduces surface porosity
- Interior application only
- No hazard labelling required

Preparation

Floor surfaces must be sound, smooth, dry and free from contaminants that may prevent adhesion.

Concrete and sand/cement screeds must be fully cured and any laitance or surface treatments must be removed prior to the application.

The surface temperature must be above 5°C when the primer is applied to the subfloor. Always ensure the subfloor is dry and incorporates an effective damp proof membrane.

Note: underfloor heating must be off for at least 48 hours prior to and following application

Applications:

Flexyfix Multi Purpose Primer can be used to promote better adhesive consumption and provide increased levels of adhesion. It will bind dust and help consolidate friable surfaces.

Stir/shake well before use and do not dilute.

Apply evenly with a roller. Coverage will be approx. 100-200ml/m².

On very porous substrates two coats can be applied always ensuring the first coat is fully dry before the second coat is applied.

Shelf Life:

18 months in unopened container when stored in a cool dry place at temperatures between 5°C and 25°C

Tools

Can be cleaned with warm water immediately after use

Note: The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.

Rewmar Limited - 51 Somers Road - Rugby CV22 7DG. UK

Tel.: 0333 800 1966 www.flexyfix.co.uk