



Flexyfix All Floors Adhesive

Issued: 20/06/2024
Page 1 of 2
Technical Data:

Base	Acrylate Mixture
Consistency	Paste
Curing System	Physical drying
Open Time*	15 - 30 min.
Drying time	Approx. 12 Hours
Specific Gravity	Approx. 1,50 g/cm ³
Temperature Resistance (cured)	-20°C to +80°C
Solid content	Approx. 76 %
Consumption	Approx. 250-600 g/m ² ; depending on subfloor and used notched trowel
Tools	Trowel A2, for (Cushion) Vinyl Trowel A3, for carpet with a latex backing, PVC flooring Trowel B1/B2, for carpet with sackcloth, actionback, polystyrene or felt backing, fibrebonded and linoleum

* This varies according to ambient conditions such as temperature, humidity, substrate etc.

Product:

Flexyfix All Floors adhesive is a single component dispersion adhesive containing synthetic resins for indoor use.

Characteristics:

- Easy to apply
- Professional quality
- Long open time
- High final bond strength
- Excellent wet-grab

Applications:

For bonding all kinds of floor covering such as carpet with foam backing, synthetic Jute (hessian) as well as vinyl, PVC and linoleum to most substrates.

Substrates:

All common porous building substrates, concrete, screed, stone and wood. Surfaces should be dry, level, sound and free of dust, residues of previously used adhesives, or any other contaminants. Surface preparation: Turn off underfloor heating in accordance with manufacturers recommendations.

Any existing floor covering must be removed.

When renovating all old adhesive residue has to be removed mechanically. Make sure the surface is sound. In cases where calcium sulphate (gypsum based) screeds are used, it is essential that the surface is abraded to remove any latience.

We recommend the application of Flexyfix Multi Purpose Primer to aid adhesion and open time of the adhesive.

We recommend a preliminary adhesion test on any substrate.

Application method


Stir well before using.

Always apply the adhesive using the correct trowel in accordance with the flooring manufacturer's recommendations.

Application temperature: +5°C to +35°C

Don't apply more adhesive than you can process within 10-20 minutes. there is no need to wait, you should insert the flooring material (vinyl, PVC, carpet with foam backing) into the still wet adhesive.

Remark: The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.



Flexyfix All Floors Adhesive

Date: 20/06/2024

Page 2 of 2

Make sure that the bond is tension free and that there are no air pockets between the adhesive layer and the flooring material. Immediately rub, press or roll the flooring well into the whole surface to achieve a good adhesive transfer. Welding of PVC floorings or linoleum is allowed at the earliest 24h after the application. Consult the installation method and technical data sheet of the flooring manufacturer. Follow the instructions of the producer for applying the floor. Restart underfloor heating (according to the recommended procedure) at the earliest 48 hours after the application.
Cleaning: Cured Adhesive can only be removed mechanically.

Packaging:

Colour: white-tan

Packaging: 15kg

Shelf life:

24 months in unopened original packaging in a dry storage place at temperatures between +5°C and +25°. Do not expose to frost.

Health- and Safety Recommendations Take the usual labour hygiene into account. Consult label and material safety data sheet for more information.

Remark: The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.